

SALES SPECIFICATION

45% Caustic Potash Membrane

<u>Property</u>	<u>Minimum</u>	<u>Maximum</u>
Total Alkalinity as KOH (wt. %)	45.00	46.00
Potassium Carbonate as K ₂ CO ₃ (wt. %)		0.10
Potassium Chloride as KCl (ppm by wt.)		50
Potassium Chlorate as KClO ₃ (ppm by wt.)		30
Potassium Sulfate as K ₂ SO ₄ (ppm by wt.)		10
Iron as Fe (ppm by wt.)		2.0
Sodium as Na (ppm by wt.)		2500
Nickel as Ni (ppm by wt.)		0.25

Produced in a non-mercury cell process.

Meets ANSI/AWWA B511-17 test requirements.

Meets Food Chemical Codex (FCC) chemical test requirements.

Caustic Potash is not produced under all cGMP requirements as defined by the FDA.

EC-CP-44615 01/26

Occidental Chemical Corporation

14555 Dallas Parkway, Suite 400
Dallas, Texas 75254
800-752-5151

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling, storage, disposal and other factors that may involve other or additional legal, environmental, safety or performance considerations, and Occidental Chemical Corporation assumes no liability whatsoever for the use of or reliance upon this information. While our technical personnel will be happy to respond to questions, safe handling and use of the product remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State, Local or Foreign laws.